



Contribution ID: 315

Type: not specified

## Comparative studies of plastic scintillator strips with high technical attenuation length for the total-body J-PET scanner

Friday, 15 July 2022 09:45 (20 minutes)

Ł. Kapłan 1, 2, 3, on behalf of the J-PET Collaboration

1 Faculty of Physics, Astronomy and Applied Computer Science, Jagiellonian University, Krakow, Poland

2 Total-Body Jagiellonian-PET Laboratory, Jagiellonian University, Krakow, Poland

3 Center for Theranostics, Jagiellonian University, Krakow, Poland

Corresponding author: lukasz.kaplon@uj.edu.pl

Plastic scintillators are used in many applications connected with advanced medical devices, for example in novel multiphoton J-PET scanners with positronium imaging capability [1, 2], and in plastic scintillation dosimetry [3].

In the first part of the lecture, results from measurements of transparency of commercially available plastic scintillators will be presented [4]. Purpose of the research is to select the best type of scintillator for the total-body J-PET scanner construction. Emission spectra, transmission spectra and technical attenuation length (TAL) values of six types of plastic scintillators with dimensions 6 mm × 24 mm × 1000 mm will be discussed. General purpose, blue-emitting plastic scintillators with low attenuation of visible light were tested: polyvinyl toluene-based BC-408, EJ-200, RP-408 and polystyrene-based Epic, SP32 and UPS-923A. The emission spectra of the investigated scintillators have maxima ranging from 420 nm to 429 nm. The BC-408 and EJ-200 scintillators have the highest transmittance values of about 90% at the maximum emission wavelength (measured through a 6 mm thick scintillator) and the highest TAL values up to about 200 cm, allowing building of long modules for total-body J-PET scanner.

In the second part of the talk, results from the research of blue- and green-emitting polystyrene-based plastic scintillators for scintillation dosimetry applications will be presented [5]. Anthracene, coumarin and perylene fluorescent dyes were used as wavelength shifters [6]. Emission maxima of manufactured green-emitting polystyrene scintillators are in range from 484 to 525 nm. The concentrations of the BPBD ultraviolet dye and Solvent Green 5 green fluorescent dye, influence the light output, rise and fall times, and the emission spectra of the scintillator samples.

### References:

- [1] P. Moskal, E. Stępień, PET Clinics 15 (2020) 439-452
- [2] P. Moskal et al., Science Advances 7 (2021) eabh4394
- [3] S. Beddar et al., 12th chapter in: M. Hamel (Ed.), Plastic Scintillators. Springer 2021
- [4] Ł. Kapłan, IEEE Transactions on Nuclear Science 67 (2020) 2286-2289
- [5] Ł. Kapłan, G. Moskal, Bio-Algorithms and Med-Systems 17 (2021) 191-197
- [6] Ł. Kapłan, G. Moskal, Submitted to Optical Materials: X (2022).

This work was supported by grant for the early stage of research financing from Centre for Technology Transfer CITTRU from the Jagiellonian University in 2021; the Priority Research Area DigiWorld under the program Excellence Initiative Research University at the Jagiellonian University in 2021; the National Science Centre of Poland through grant OPUS No. 2019/35/B/ST2/03562, and the Jagiellonian University under project No. CRP/0641.221.2020. The authors acknowledge support by the TEAM POIR.04.04.00-00-4204/17 program, the

National Science Center grant no. 2021/42/A/ST2/00423 and the SciMat and qLife Priority Research Areas budget under the program Excellence Initiative - Research University at the Jagiellonian University.

**Presenter:** Dr KAPŁON; JAGIELLONIAN UNIVERSITY, POLAND, Łukasz

**Session Classification:** Session 1